

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
19 December 2002 (19.12.2002)

PCT

(10) International Publication Number
WO 02/100909 A1

- (51) International Patent Classification⁷: C08F 10/08, 4/642 (74) Agents: COLUCCI, Giuseppe et al.; Basell Poliolefine Italia S.p.A., Intellectual Property, P.le G. Donegani, 12, I-44100 Ferrara (IT).
- (21) International Application Number: PCT/EP02/06575 (81) Designated States (*national*): JP, US.
- (22) International Filing Date: 11 June 2002 (11.06.2002) (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR).
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 01202263.8 12 June 2001 (12.06.2001) EP
- (71) Applicant (*for all designated States except US*): BASELL POLYOLEFINE GMBH [DE/DE]; Brühler Strasse 60, 50389 Wesseling, Germany (DE).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): RESCONI, Luigi [IT/IT]; Via Arianuova, 56/B, I-44100 Ferrara (IT).
- Declarations under Rule 4.17:**
— *as to the applicant's entitlement to claim the priority of the earlier application (Rule 4.17(iii)) for all designations of inventorship (Rule 4.17(iv)) for US only*
- Published:**
— *with international search report*
— *before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments*

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

WO 02/100909 A1

(54) Title: PROCESS FOR THE POLYMERIZATION OF 1-BUTENE


(57) Abstract: A process for polymerizing 1-butene comprising the step of contacting under polymerization " conditions 1-butene and optionally from 0 to 20% by mol of an alpha olefin with a catalyst system obtainable by contacting a bridged metallocene compound of formula (I) wherein R¹ and R² are an hydrocarbon radical A is a carbon atom, a germanium atom or a silicon atom; m is 1, 2; M is a metal of group 4 of the Periodic Table of the Elements; X, is hydrogen, a halogen atom, or a group R, OR, OSO₂CF₃, OCOR, SR, NR₂ or PR₂, wherein the substituents R are hydrocarbon radical; L is a moiety of formula (IIa), (IIb), or (IIc) wherein T is an oxygen (O) or sulphur (S) atom or a CH₂ group; and R³, R⁴, R⁵, R⁶, R⁷, R⁸ are hydrogen or hydrocarbon radicals; one or more alumoxanes or compounds able to form an alkylmetallocene cation; and optionally an organo aluminum compound.

PROCESS FOR THE POLYMERIZATION OF 1-BUTENE

The present invention relates to a process for polymerizing 1-butene by using a substituted bis cyclopentadienyl bridged metallocene compound. 1-butene polymers are well known in the art. In view of their good properties in terms of pressure resistance, creep resistance, and impact strength they have a lot of uses such as the manufacture of pipes to be used in the metal pipe replacement, easy-open packaging and films. The 1-butene (co)polymers are generally prepared by polymerizing 1-butene in the presence of TiCl_3 based catalysts components together with diethylaluminum chloride (DEAC) as cocatalyst. In some cases diethyl aluminum iodide (DEAI) is also used in mixtures with DEAC. The polymers obtained, however, generally do not show satisfactory mechanical properties. Furthermore, in view of the low yields obtainable with the TiCl_3 based catalysts, the 1-butene polymers prepared with these catalysts have a high content of catalyst residues (generally more than 300 ppm of Ti) which lowers the properties of the polymers making it necessary a deashing step. 1-butene (co)polymers can also be obtained by polymerizing the monomers in the presence of a stereospecific catalyst comprising (A) a solid component comprising a Ti compound and an electron-donor compound supported on MgCl_2 ; (B) an alkylaluminum compound and, optionally, (C) an external electron-donor compound. A process of this type is disclosed in EP-A-172961 and more recently in WO99/45043. In *Macromolecules* 1995, 28, 1739-1749 *rac*-dimethylsilylbis(4,5,6,7-tetrahydro-1-indenyl)zirconium dichloride and methylaluminoxane have been used for polymerizing 1-butene, even if the yield of the process is not indicated the molecular weight of the polymer (M_n) is very low. Recently metallocene compounds have been used for producing 1-butene polymers. In *Macromol. Rapid Commun.* 18, 581-589 (1997) *rac* and *meso*-[dimethylsilylenebis(2,3,5-trimethyl-cyclopentadienyl)]zirconium dichloride have been used for the polymerization of 1-butene, the yields of the process and the molecular weight of the obtained polymers are rather low. More recently in *Macromolecules* 2000, 33, 1955-1956 $\text{Me}_2\text{Si}(2\text{-Me-4,5-BzoInd})_2\text{ZrCl}_2$, $\text{Me}_2\text{Si}(2\text{-Me-4-PhInd})_2\text{ZrCl}_2$ and $\text{Me}_2\text{Si}(\text{Ind})_2\text{ZrCl}_2$ have been tested in the polymerization of 1-butene. Even if the molecular weights of the polymers appear to be quite high, the activities of these catalysts are low as shown in the comparative examples of the present application. A new process that permits to obtain 1-butene polymer with high molecular weight and in high yield is therefore desirable. An object of the present invention is a process for polymerizing 1-butene comprising the step of contacting under polymerization conditions 1-butene and optionally from 0 to 20% by mol, preferably from 0

to 10% by mol of ethylene, propylene and/or an alpha olefin of formula $\text{CH}_2=\text{CHZ}$ wherein Z is a $\text{C}_3\text{-C}_{10}$ alkyl group, in the presence of a catalyst system obtainable by contacting:

- a) a racemic or racemic-like bridged metallocene compound of formula (I)



wherein

R^1 , same or different, is hydrogen, a linear or branched saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_3\text{-C}_{20}$ -cycloalkyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -alkylaryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; preferably R^1 is hydrogen or a $\text{C}_1\text{-C}_{20}$ -alkyl radical, more preferably R^1 is hydrogen or methyl.

A, same or different, is a carbon atom, a germanium atom or a silicon atom; with the proviso that, when m is 1, A is different from a carbon atom; preferably A is a silicon atom;

m is 1 or 2, preferably m is 1;

R^2 , same or different, is hydrogen, or a linear or branched saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_3\text{-C}_{20}$ -cycloalkyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -alkylaryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; preferably R^2 is hydrogen, a $\text{C}_1\text{-C}_{20}$ -alkyl or a $\text{C}_6\text{-C}_{20}$ -aryl; more preferably R^2 is hydrogen, methyl or phenyl;

more preferably the bridge $(\text{R}^2\text{A})_m$ is $\text{Si}(\text{CH}_3)_2$, SiPh_2 , CH_2CH_2 ;


M is a transition metal atom selected from those belonging to group 4 of the Periodic Table of the Elements (IUPAC version); preferably M is zirconium or hafnium, more preferably M is zirconium;

X, same or different, is a hydrogen atom, a halogen atom, or a R, OR, OSO_2CF_3 , OCOR, SR, NR_2 or PR_2 group, wherein R is a linear or branched, saturated or unsaturated


C₁-C₂₀ alkyl, C₃-C₂₀ cycloalkyl, C₆-C₂₀ aryl, C₇-C₂₀ alkylaryl or C₇-C₂₀ arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements; or two X can optionally form a substituted or unsubstituted butadienyl radical or a OR¹¹O group wherein R¹¹ is a divalent radical selected from C₁-C₂₀ alkylidene, C₆-C₄₀ arylidene, C₇-C₄₀ alkylarylidene and C₇-C₄₀ arylalkylidene radicals; preferably X is a hydrogen atom, a halogen atom or a R group; more preferably X is chlorine or a methyl radical;

wherein the R substituents are selected from linear or branched, saturated or unsaturated C₁-C₂₀-alkyl, C₃-C₂₀-cycloalkyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl, C₇-C₂₀-arylalkyl radical, optionally containing heteroatoms belonging to groups 13 or 15-17 of the Periodic Table of the Elements; preferably X is hydrogen, a halogen atom, a R or OR group; more preferably X is hydrogen, chlorine or methyl;


L, same or different, is a moiety of formula (IIa), (IIb), or (IIc):



(IIa)



(IIb)



(IIc)

wherein

in the moiety of formula (IIa) T bonds to the cyclopentadienyl group in position 5;

in the moiety of formula (IIb) N bonds to the cyclopentadienyl group in position 4;

in the moiety of formula (IIc) the carbon atom marked with the symbol * bonds to the cyclopentadienyl group in position 4;

T is an oxygen (O) atom, a sulphur (S) atom or a CH₂ group; preferably T is sulphur;

R³ is hydrogen or a linear or branched, saturated or unsaturated C₁-C₂₀-alkyl, C₃-C₂₀-cycloalkyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl, C₇-C₂₀-arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

R⁴ is a linear or branched saturated or unsaturated C₁-C₂₀-alkyl, C₃-C₂₀-cycloalkyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl, C₇-C₂₀-arylalkyl radical, optionally containing heteroatoms

belonging to groups 13-17 of the Periodic Table of the Elements;

preferably, R^3 is hydrogen or a C_1 - C_{20} -alkyl radical; more preferably R^3 is methyl;


preferably, R^4 is a C_1 - C_{20} -alkyl radical; more preferably R^4 is methyl;

R^5 , R^6 , R^7 , R^8 and R^9 , same or different, are selected from the group consisting of hydrogen, a linear or branched saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements, or two adjacent groups can form together a saturated or unsaturated condensed 5 or 6 membered ring optionally containing heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements; Preferably R^7 is hydrogen or methyl; preferably R^5 , R^6 , R^8 and R^9 are hydrogen.

- b) an alumoxane or a compound able to form an alkylmetallocene cation; and
- c) optionally an organo aluminum compound.


Preferred structures for the $(R^2_2A)_m$ bridging group are $Si(CH_3)_2$, $SiPh_2$, CH_2CH_2 , the $Si(CH_3)_2$ being the most preferred.

Non limitative examples of compound of formula (I) are:



as well as the corresponding dihydride and dimethyl compounds.

Preferably the compounds of formula (I) have formula (III):




(III)

wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , A, M, T, X and m are defined as above.


Metallocene compounds of formula (I) or (III) are well known in the art, they can be prepared according to known procedure, such as those described in WO 01/44318 and USP 5,786,432. Alumoxanes used as component b) can be obtained by reacting water with an organo-aluminium compound of formula H_jAlU_{3-j} or $H_jAl_2U_{6-j}$, where U substituents, same or different, are hydrogen atoms, C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl or C_7 - C_{20} -arylalkyl, optionally containing silicon or germanium atoms with the proviso that at least one U is different from halogen, and j ranges from 0 to 1, being also a non-integer number. In this reaction the molar ratio of Al/water is preferably comprised between 1:1 and 100:1. The molar ratio between aluminium and the metal of the metallocene is comprised between about 10:1 and about 20000:1, and more preferably between about 100:1 and about 5000:1.

The alumoxanes used in the catalyst according to the invention are considered to be linear, branched or cyclic compounds containing at least one group of the type:




wherein the substituents U, same or different, are described above.

In particular, alumoxanes of the formula:



can be used in the case of linear compounds, wherein n^1 is 0 or an integer from 1 to 40 and the substituents U are defined as above, or alumoxanes of the formula:



can be used in the case of cyclic compounds, wherein n^2 is an integer from 2 to 40 and the U substituents are defined as above. Examples of alumoxanes suitable for use according to the present invention are methylalumoxane (MAO), tetra-(isobutyl)alumoxane (TIBAO), tetra-(2,4,4-trimethyl-pentyl)alumoxane (TIOAO), tetra-(2,3-dimethylbutyl)alumoxane (TDMBAO) and tetra-(2,3,3-trimethylbutyl)alumoxane (TTMBAO). Particularly interesting cocatalysts are those described in WO 99/21899 and in PCT/EP00/09111 in which the alkyl and aryl groups have specific branched patterns. Non-limiting examples of aluminium compounds according to said international applications are:

tris(2,3,3-trimethyl-butyl)aluminium, tris(2,3-dimethyl-hexyl)aluminium, tris(2,3-dimethyl-butyl)aluminium, tris(2,3-dimethyl-pentyl)aluminium, tris(2,3-dimethyl-heptyl)aluminium, tris(2-methyl-3-ethyl-pentyl)aluminium, tris(2-methyl-3-ethyl-hexyl)aluminium, tris(2-methyl-3-ethyl-heptyl)aluminium, tris(2-methyl-3-propyl-hexyl)aluminium, tris(2-ethyl-3-methyl-butyl)aluminium, tris(2-ethyl-3-methyl-pentyl)aluminium, tris(2,3-diethyl-pentyl)aluminium, tris(2-propyl-3-methyl-butyl)aluminium, tris(2-isopropyl-3-methyl-butyl)aluminium, tris(2-isobutyl-3-methyl-pentyl)aluminium, tris(2,3,3-trimethyl-pentyl)aluminium, tris(2,3,3-trimethyl-hexyl)aluminium, tris(2-ethyl-3,3-dimethyl-butyl)aluminium, tris(2-ethyl-3,3-dimethyl-pentyl)aluminium, tris(2-isopropyl-3,3-dimethyl-butyl)aluminium, tris(2-trimethylsilyl-propyl)aluminium, tris(2-methyl-3-phenyl-butyl)aluminium, tris(2-ethyl-3-phenyl-butyl)aluminium, tris(2,3-dimethyl-3-phenyl-butyl)aluminium, tris(2-phenyl-propyl)aluminium, tris[2-(4-fluoro-phenyl)-propyl]aluminium, tris[2-(4-chloro-phenyl)-propyl]aluminium, tris[2-(3-isopropyl-phenyl)-propyl]aluminium, tris(2-phenyl-butyl)aluminium, tris(3-methyl-2-phenyl-butyl)aluminium, tris(2-phenyl-pentyl)aluminium,

tris[2-(pentafluorophenyl)-propyl]aluminium, tris[2,2-diphenyl-ethyl]aluminium and tris[2-phenyl-2-methyl-propyl]aluminium, as well as the corresponding compounds wherein one of the hydrocarbyl groups is replaced with a hydrogen atom, and those wherein one or two of the hydrocarbyl groups are replaced with an isobutyl group. Amongst the above aluminium compounds, trimethylaluminium (TMA), triisobutylaluminium (TIBAL), tris(2,4,4-trimethyl-pentyl)aluminium (TIOA), tris(2,3-dimethylbutyl)aluminium (TDMBA) and tris(2,3,3-trimethylbutyl)aluminium (TTMBA) are preferred. Non-limiting examples of compounds able to form an alkylmetallocene cation are compounds of formula D^+E^- , wherein D^+ is a Brønsted acid, able to donate a proton and to react irreversibly with a substituent X of the metallocene of formula (I) and E^- is a compatible anion, which is able to stabilize the active catalytic species originating from the reaction of the two compounds, and which is sufficiently labile to be able to be removed by an olefinic monomer. Preferably, the anion E^- comprises of one or more boron atoms. More preferably, the anion E^- is an anion of the formula $BAr_4^{(c)}$, wherein the substituents Ar which can be identical or different are aryl radicals such as phenyl, pentafluorophenyl or bis(trifluoromethyl)phenyl. Tetrakis-pentafluorophenyl borate is particularly preferred examples of these compounds are described in WO 91/02012. Moreover, compounds of the formula BAr_3 can conveniently be used. Compounds of this type are described, for example, in the published International patent application WO 92/00333. Other examples of compounds able to form an alkylmetallocene cation are compounds of formula BAR_3P wherein P is a substituted or unsubstituted pyrrol radicals. These compounds are described in PCT/EP01/01467. all these compounds containing boron atoms can be used in a molar ratio between boron and the metal of the metallocene comprised between about 1:1 and about 10:1; preferably 1:1 and 2:1; more preferably about 1:1.

Non limiting examples of compounds of formula D^+E^- are:

Triethylammoniumtetra(phenyl)borate,
Tributylammoniumtetra(phenyl)borate,
Trimethylammoniumtetra(tolyl)borate,
Tributylammoniumtetra(tolyl)borate,
Tributylammoniumtetra(pentafluorophenyl)borate,
Tributylammoniumtetra(pentafluorophenyl)aluminate,
Tripropylammoniumtetra(dimethylphenyl)borate,
Tributylammoniumtetra(trifluoromethylphenyl)borate,

Tributylammoniumtetra(4-fluorophenyl)borate,
 N,N-Dimethylaniliniumtetra(phenyl)borate,
 N,N-Diethylaniliniumtetra(phenyl)borate,
 N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)borate,
 N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)aluminate,
 Di(propyl)ammoniumtetrakis(pentafluorophenyl)borate,
 Di(cyclohexyl)ammoniumtetrakis(pentafluorophenyl)borate,
 Triphenylphosphoniumtetrakis(phenyl)borate,
 Triethylphosphoniumtetrakis(phenyl)borate,
 Diphenylphosphoniumtetrakis(phenyl)borate,
 Tri(methylphenyl)phosphoniumtetrakis(phenyl)borate,
 Tri(dimethylphenyl)phosphoniumtetrakis(phenyl)borate,
 Triphenylcarbeniumtetrakis(pentafluorophenyl)borate,
 Triphenylcarbeniumtetrakis(pentafluorophenyl)aluminate,
 Triphenylcarbeniumtetrakis(phenyl)aluminate,
 Ferroceniumtetrakis(pentafluorophenyl)borate,
 Ferroceniumtetrakis(pentafluorophenyl)aluminate.
 Triphenylcarbeniumtetrakis(pentafluorophenyl)borate,
 N,N-Dimethylaniliniumtetrakis(pentafluorophenyl)borate.

Further compounds that can be used are those of formula $RM'-O-M'R$, R being an alkyl or aryl group, and M' is selected from an element of the Group 13 of the Periodic Table of the Elements (new IUPAC version). Compounds of this type are described, for example, in the International patent application WO 99/40129. Organic aluminum compounds used as compound c) are those of formula H_jAlU_{3-j} or $H_jAl_2U_{6-j}$ described above. The polymerization process of the present invention can be carried out in liquid phase, optionally in the presence of an inert hydrocarbon solvent, or in gas phase. Said hydrocarbon solvent can be either aromatic (such as toluene) or aliphatic (such as propane, hexane, heptane, isobutane, cyclohexane and 2,2,4-trimethylpentane). Preferably the polymerization is carried out in liquid monomer. The polymerization temperature preferably ranges from 0°C to 250°C; preferably comprised between 20°C and 150°C and, more particularly between 40°C and 90°C; The molecular weight distribution of the polymer obtained with the process of the present invention can be varied by using mixtures of different metallocene compounds or

mixtures of the metallocene compound of formula (I) and a Ziegler-Natta catalyst or by carrying out the polymerization in several stages at different polymerization temperatures and/or different concentrations of the molecular weight regulators and/or different monomer concentration. The polymerization yield depends on the purity of the transition metal organometallic catalyst compound a) in the catalyst, therefore, said compound can be used as such or can be subjected to purification treatments before use. With the process of the present invention 1-butene can be polymerized with high yields and the isotactic polymers obtained show a high molecular weight and a low content of regioerrors, i.e. 4,1 insertions. Moreover the obtained polymer show very high values of the flexural modulus allowing to obtain pipes having a longer durability and thinner walls. Therefore another object of the present invention is a 1-butene homopolymer having the following characteristics:

- intrinsic viscosity (I.V.) > 0.7 dL/g; preferably >1 dL/g; more preferably >1.5 dL/g;
- isotactic triads (mm) > 70%; preferably >95%; more preferably >98%;
- a flexural modulus (ASTM D 638) > 400 Mpa; preferably > 425 MPa; more preferably > 450 Mpa;
- melting point >105°C, preferably > 108°C; more preferably >110°C.

The 4,1 insertions are lower than < 0.90%; preferably the 4,1 insertions are comprised between 0.05% and 0.90%; more preferably they are comprised between 0.10% and 0.70%; a further preferred range is between 0.10% and 0.39%.

Preferably the 1-butene homopolymers of the invention have molecular weight distribution (Mw/Mn) <3; more preferably < 2.5; even more preferably < 2.2 .

When 1-butene is copolymerized with ethylene, propylene or an alpha olefin of formula $\text{CH}_2=\text{CHZ}$ wherein Z is a $\text{C}_3\text{-C}_{10}$ alkyl group, a copolymer having a comonomer derived units content from 0 to 50% by weight can be obtained. preferably from 0.5 to 20% by weight. Preferred comonomers are ethylene or propylene.

A particular interesting copolymer that can be obtained with the process of the present invention is a 1-butene/ethylene copolymer having a content of ethylene derived units from 0.1% to 5 % by weight preferably from 0.5% to 2.5 % by weight in which the ethylene content in the polymer (C_2) and the melting point of the polymer (T_m) meet the following relation:

$$\text{T}_m < -0.3283\text{C}_2^3 + 4.7184 \text{C}_2^2 - 22.454 \text{C}_2 + 114.$$

Preferably the relation is $\text{T}_m < -0.3283\text{C}_2^3 + 4.7184 \text{C}_2^2 - 22.454 \text{C}_2 + 113$; more preferably $\text{T}_m < -0.3283\text{C}_2^3 + 4.7184 \text{C}_2^2 - 22.454 \text{C}_2 + 111.2$.

When the content of ethylene derived units in the above copolymer ranges from 0.1 to 2.5 % by weight the ethylene content in the polymer (C_2) and the melting point of the polymer (T_m) meet the following relation:

$$T_m = 4.0037C_2^2 - 21.91C_2 + 114;$$

preferably the relation is $T_m = 4.0037C_2^2 - 21.91C_2 + 113$; more preferably $T_m = 4.0037C_2^2 - 21.91C_2 + 110.5$.

Furthermore the 1-butene/ethylene copolymer above described are endowed with a molecular weight distribution (M_w/M_n) <4.

A further feature of said 1-butene/ethylene copolymer is the intrinsic viscosity (I.V.) > 0.7 dL/g; preferably >1 dL/g.

Experimental section

The intrinsic viscosity (I.V.) was measured in tetrahydronaphthalene (THN) at 135°C.

The melting points of the polymers (T_m) were measured by Differential Scanning Calorimetry (D.S.C.) on a Perkin Elmer DSC-7 instrument, according to the standard method. A weighted sample (5-10 mg) obtained from the polymerization was sealed into aluminum pans and heated at 180°C with a scanning speed corresponding to 10°C/minute. The sample was kept at 180°C for 5 minutes to allow a complete melting of all the crystallites. Successively, after cooling to 20°C with a scanning speed corresponding to 10°C/minute. After standing 2 minutes at 20°C, the sample was heated for the second time at 180°C with a scanning speed corresponding to 10°C/min. In this second heating run, the peak temperature was taken as the melting temperature (T_m) and the area as global melting enthalpy (ΔH_f).

The molecular weight distribution was determined on a WATERS 150 C using the following chromatographic conditions:


Columns:	3x SHODEX AT 806 MS; 1x SHODEX UT 807; 1x SHODEX AT-G;
Solvent:	1,2,4 trichlorobenzene (+ 0.025% 2,6-Di-tert.Butyl-4-Methyl-Phenol);
Flow rate:	0.6 - 1 ml/min;
Temperature:	135 °C;
Detector:	INFRARED AT $\lambda \approx 3.5 \mu\text{m}$;
Calibration:	Universal Calibration with PS-Standards.

^{13}C -NMR spectra were acquired on a DPX-400 spectrometer operating at 100.61 MHz in the Fourier transform mode at 120 °C. The peak of the 2B_2 carbon (nomenclature according to Carman, C. J.; Harrington, R. A.; Wilkes, C. E. *Macromolecules* 1977, 10, 535) was used as

internal reference at 27.73. The samples were dissolved in 1,1,2,2-tetrachloroethane-*d*₂ at 120 °C with a 8% wt/v concentration. Each spectrum was acquired with a 90° pulse, 15 seconds of delay between pulses and CPD (waltz16) to remove ¹H-¹³C coupling. About 3000 transients were stored in 32K data points using a spectral window of 6000 Hz. Assignments of 4,1 insertion were made according to Busico (V. Busico, R. Cipullo, A. Borriello, *Macromol. Rapid. Commun.* 1995, 16, 269-274)

Chemical Shift (ppm)	Carbon	Sequence
40.21	CH ₂ (S _{αα})	B
39.65	CH ₂	D1
37.3	CH	D2
34.99	CH	B
34.31	CH ₂	D3
31.13	CH ₂	D5
27.73	CH ₂ branch	B mmmmm
27.57	CH ₂ branch	B mmmmr
27.37	CH ₂ branch	B mmrrr
27.21-27.14	CH ₂	D4+D6
26.57	CH ₂ branch	B mrrrm
10.96	CH ₃	B

The content of 4,1 insertions was calculated as follows: 4,1 units = $0.5 \times I_4 \times 100 / (I_2 + I_4)$



Preparation of catalyst components

Rac dimethylsilandiylbis-6-[2,5-dimethyl-3-(2'-methyl-phenyl)cyclopentadienyl-[1,2-b]-thiophene]zirconium dichloride (A-1), rac dimethylsilandiylbis-6-[2,5-dimethyl-3-(2',5'-

dimethyl-phenyl)cyclopentadienyl-[1,2-b]-thiophene]zirconium dichloride (A-2) and rac dimethylsilylindylbis-6-(2,5-dimethyl-3-phenylcyclopentadienyl-[1,2-b]-thiophene)zirconium dichloride (A-3) were prepared according to PCT/EP00/12406. Rac dimethylsilylbis(2-methyl-4-phenyl-indenyl) zirconium dichloride (A-4) was prepared according to USP 5,786,432. The cocatalyst methylalumoxane (MAO) was a commercial product which was used as received (Witco AG, 10 %wt/vol toluene solution, 1.7 M in Al).

Examples 1-4 and comparative examples 5-6 1-butene homopolymer

The catalyst mixture was prepared by dissolving the amount of the metallocene indicated in table 1 in 8 ml of toluene (excepting for example 3 in which 3 ml of toluene has been used) with the proper amount of the MAO solution (amounts are reported in table 1), obtaining a solution which was stirred for 10 min at room temperature before being injected into the autoclave.

4 mmol of $\text{Al}(i\text{-Bu})_3$ (TIBA) (as a 1 M solution in hexane) and 712 g of 1-butene were charged, at room temperature, in a 2.3-L jacketed stainless-steel autoclave, equipped with magnetically driven stirrer and a 35-mL stainless-steel vial, connected to a thermostat for temperature control. The autoclave was then thermostatted at 2 °C below the polymerization temperature and the catalyst system, prepared as reported above, was injected in the autoclave by means of nitrogen pressure through the stainless-steel vial. The temperature was rapidly raised to the polymerization temperature and the polymerization was carried out at constant temperature, for a time indicated in table 1. After cooling the reactor to room temperature, the polymer was dried under reduced pressure, at 60 °C. The polymerization conditions and the characterization data of the obtained polymers are reported in Table 1.

Examples 7-13 1-butene homopolymer

The catalyst mixture was prepared by dissolving the amount of the metallocene indicated in table 2 in 8 ml of toluene with the proper amount of the MAO solution (Al/Zr ratio reported in table 2), obtaining a solution which was stirred for 10 min at room temperature before being injected into the autoclave. A 4.25 litres steel autoclave, equipped with magnetically stirred anchor (usual stirring rate 550 rpm) and with different Flow Record & Control systems (FRC), among which a FRC having maximum flow rate of 9000 gr/hour for 1-butene and two FRC having maximum flow rate of 500 and 30 g/h for ethylene is cleaned with warm nitrogen (1.5 barg N_2 , 70°C, 1 hour). After the above mentioned autoclave cleaning, the stirring starts and 1-butene is fed into the reactor (1350 gr at 30°C) together with 6 mmol of $\text{Al}(i\text{-Bu})_3$ (TIBA) (as a 1 M solution in hexane). Subsequently, the reactor inner

temperature is raised from 30°C to the polymerisation temperature (indicated in table 2); as a consequence the pressure increases. When pressure and temperature are constant, the catalytic solution is fed into the reactor with a nitrogen overpressure. The polymerisation is run for a time indicated in table 2 at the chosen polymerization temperature. Then the stirring is interrupted; the pressure into the autoclave is raised to 20 bar-g with nitrogen. The bottom discharge valve is opened and the 1-butene/poly-1-butene mixture is discharged into the steel heated tank containing water at 70°C. The tank heating is switched off and a flux of 0.5 bar-g nitrogen is fed. After 1 hour cooling at room temperature the steel tank is opened and the wet polymer collected. The wet polymer is dried in oven under nitrogen at 70°C. The polymerization conditions and the characterization data of the obtained polymers are reported in Table 2.

Characterization of homopolymer

Samples of polymer obtained from examples 3, 7, 9, and 10 were ground in an electric mill with liquid nitrogen in order to achieve the right size to feed them in a Brabender® mixer chamber. The ground samples were mixed in a Brabender® chamber with 1% 2,6-di-*t*-butyl-4-methyl phenol (BHT) at 200°C and then transformed in 1.9 and 4.0 mm thick plaques through compression molding at 200°C.

The 1.9 mm thick plaques were submitted to tensile test (according to ASTM D 638 method), while the 4.0 mm thick plaques were submitted to the flexural modulus determination according to ISO 178 method. The results are reported in table 2a.

Examples 14- 19 1-butene/ethylene copolymer

The catalyst mixture was prepared by dissolving the amount of the metallocene indicated in table 2 in toluene with the proper amount of the MAO solution ($Al/Zr = 10000$), obtaining a solution which was stirred for 10 min at room temperature before being injected into the autoclave. A 4.25 litres steel autoclave, equipped with magnetically stirred anchor (usual stirring rate 550 rpm) and with the proper Flow Record & Control systems (FRC), among which a FRC having maximum flow rate of 9000 gr/hour for 1-butene and two FRC having maximum flow rate of 500 and 30 g/h for ethylene is cleaned with warm nitrogen (1.5 barg N_2 , 70°C, 1 hour). After the above mentioned autoclave cleaning, the stirring starts, 1-butene is fed into the reactor (1350 gr at 30°C excepting for example 10 wherein 1368 g of 1-butene are used) with the amount of ethylene reported in table 3, together with 6 mmol of $Al(i-Bu)_3$ (TIBA) (as a 1 M solution in hexane). Subsequently, the reactor inner temperature is raised

from 30°C to the polymerisation temperature (indicated in table 3); as a consequence the pressure increases. When pressure and temperature are constant, the catalytic solution is fed into the reactor with a nitrogen overpressure and the polymerisation pressure is kept constant feeding only ethylene (amount indicated in table 3). The polymerisation is run for a time indicated in table 3 at the chosen polymerization temperature. Then the stirring is interrupted; the pressure into the autoclave is raised to 20 bar-g with nitrogen. The bottom discharge valve is opened and the 1-butene/poly-1-butene mixture is discharged into the steel heated tank containing water at 70°C. The tank heating is switched off and a flux of 0.5 bar-g nitrogen is fed. After 1 hour cooling at room temperature the steel tank is opened and the wet polymer collected. The wet polymer is dried in a oven under nitrogen at 70°C. The polymerization conditions and the characterization data of the obtained polymers are reported in Table 3

Table 1

Ex	metall.	Mg	Al _(MAO) /Zr	T _{pol} °C	t (min)	Yield (g)	Activity kg/(g _{cat} ·h)	I.V. (dL/g)	M _w /M _n	triads % (mm)	regioerrors 4,1 insertions	T _m (II) °C	ΔH _f (II) J/g
1	A-1	2	1000	60	17	73.8	130.2	1.8	n.a.	>99	0.17%	110	40
2	A-1	3	200	60	30	89.9	60.0	2.0	n.a.	≈100	0.3%	n.a.	n.a.
3	A-2	1	1000	60	60	69.9	69.9	1.7	2.16	≈100	0.2%	111	34
4	A-2	3	200	70	30	124.9	83.3	1.3	n.a.	n.a.	n.a.	n.a.	n.a.
5*	A-3	4	1000	60	30	96.5	48.3	1.0	2.12	≈100	1%	100	37
6*	A-4	4	1000	60	60	39.5	9.9	0.9	n.a.	≈100	0.4%	105	33

*comparative

n.a. = not available

Table 2

Ex	Metall.	Mg	Al _(MAO) /Zr	T _{pol}	t (min)	Yield (g)	Activity kg/(g _{cat} ·h)	I.V. (dL/g)	M _w /M _n	T _m (II) °C	ΔH _f (II) J/g
7	A-2	3	1000	50	43	263	122.3	2.31	2.09	111.6	36.0
8	A-2	1	1000	70	60	130	130.0	1.50	2.18	109.2	35.4
9	A-2	1	1000	85	60	195	195.0	n.a.	2.12	n.a.	n.a.
10	A-1	3	1000	50	53	285	107.5	2.72	2.14	110.2	34.9
11	A-1	2	1000	85	60	90	45.0	n.a.	2.12	n.a.	n.a.
12	A-1	2	1000	85	60	312.4	156.2	n.a.	2.18	n.a.	n.a.
13	A-1	2	500	85	60	166	83.0	n.a.	2.16	n.a.	n.a.

Table 2a

Ex	Flexural modulus (MPa)	Yield strength (MPa)	Break strength (MPa)	Elongation at break (%)
3	480	n.a.	n.a.	n.a.
7	472	19.2	40.0	300
9	472	23.8	22.8	218
10	437	18.6	37.9	280

n.a.=not available


Table 3

Ex	met.	mg	T _{pol} °C	t (min)	C ₂ added g	C ₂ feed g	yield (g)	Activity kg/ (g _{cat} ·h)	I.V.	C ₂ wt% (IR)	M _w /M _n	T _m (II) °C
14	A-1	1	70	70	0.9	4	224.0	192.0	1.22	0.50	2.41	99.56
15	A-1	1	70	70	0.8	6	127.0	108.9	1.26	0.50	2.40	99.72
16	A-1	1	70	70	2.6	17	432.0	370.3	1.09	1.90	2.68	78.90
17	A-2	1	70	70	1.1	0.4	96.0	82.3	1.17	0.70	2.52	96.02
18	A-2	1	70	70	2.3	4.6	203.0	174.0	1.41	2.20	3.92	81.00
19	A-2	1	70	70	3.0	17	340.0	291.4	1.17	1.70	2.91	83.84

C₂ added = ethylene added in the reactor with 1-buteneC₂ feed = ethylene feed during the polymerization

CLAIMS

1. A process for polymerizing 1-butene comprising the step of contacting under polymerization conditions 1-butene and optionally from 0 to 20% by mol, of ethylene, propylene and/or an alpha olefin of formula $\text{CH}_2=\text{CHZ}$ wherein Z is a $\text{C}_3\text{-C}_{10}$ alkyl group, in the presence of a catalyst system obtainable by contacting:
- a) a racemic or racemic-like bridged metallocene compound of formula (I)



wherein

R^1 , same or different, is hydrogen, a linear or branched saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_3\text{-C}_{20}$ -cycloalkyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -alkylaryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

A, same or different, is a carbon atom, a germanium atom or a silicon atom; with the proviso that when m is 1 A is different from a carbon atom;

m is 1, 2,


R^2 , same or different, is hydrogen, a linear or branched saturated or unsaturated $\text{C}_1\text{-C}_{20}$ -alkyl, $\text{C}_3\text{-C}_{20}$ -cycloalkyl, $\text{C}_6\text{-C}_{20}$ -aryl, $\text{C}_7\text{-C}_{20}$ -alkylaryl, $\text{C}_7\text{-C}_{20}$ -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

M is a transition metal atom selected from those belonging to group 4 of the Periodic Table of the Elements (IUPAC version);


X, same or different, is a hydrogen atom, a halogen atom, or a R, OR, OSO_2CF_3 , OCOR, SR, NR_2 or PR_2 group, wherein R is a linear or branched, saturated or unsaturated $\text{C}_1\text{-C}_{20}$ alkyl, $\text{C}_3\text{-C}_{20}$ cycloalkyl, $\text{C}_6\text{-C}_{20}$ aryl, $\text{C}_7\text{-C}_{20}$ alkylaryl or $\text{C}_7\text{-C}_{20}$ arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of

the Periodic Table of the Elements; or two X can optionally form a substituted or unsubstituted butadienyl radical or a $OR^{11}O$ group wherein R^{11} is a divalent radical selected from C_1 - C_{20} alkylidene, C_6 - C_{40} arylidene, C_7 - C_{40} alkylarylidene and C_7 - C_{40} arylalkylidene radicals; the R substituents are selected from linear or branched, saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radical, optionally containing heteroatoms belonging to groups 13 or 15-17 of the Periodic Table of the Elements;


L, same or different, is a moiety of formula (IIa), (IIb), or (IIc)



(IIa)



(IIb)



(IIc)

wherein

in the moiety of formula (IIa) T bonds to the cyclopentadienyl group in position 3;

in the moiety of formula (IIb) N bonds to the cyclopentadienyl group in position 4;

in the moiety of formula (IIc) the carbon atom marked with the symbol * bonds to the cyclopentadienyl group in position 4;

T is an oxygen (O) atom or a sulphur (S) atom or a CH_2 group;

R^3 is hydrogen, a linear or branched saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

R^4 is a linear or branched saturated or unsaturated C_1 - C_{20} -alkyl, C_3 - C_{20} -cycloalkyl, C_6 - C_{20} -aryl, C_7 - C_{20} -alkylaryl, C_7 - C_{20} -arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements;

R^5 , R^6 , R^7 , R^8 and R^9 same or different are selected from the group consisting of

hydrogen, linear or branched saturated or unsaturated C₁-C₂₀-alkyl, C₃-C₂₀-cycloalkyl, C₆-C₂₀-aryl, C₇-C₂₀-alkylaryl, C₇-C₂₀-arylalkyl radical, optionally containing heteroatoms belonging to groups 13-17 of the Periodic Table of the Elements or two adjacent groups can form together a saturated or unsaturated condensed 5 or 6 membered ring optionally containing heteroatoms belonging to groups 13-16 of the Periodic Table of the Elements;


b) an alumoxane or a compound able to form an alkylmetallocene cation; and

c) optionally an organo aluminum compound.

2. The process according to claim 1 wherein in the bridged metallocene compound of formula (I):

R¹ is selected from the group consisting of hydrogen, C₁-C₂₀-alkyl radical; R² is selected from hydrogen C₁-C₂₀-alkyl or C₆-C₂₀-aryl; m is 1; A is a silicon atom; M is zirconium, hafnium; X is halogen, a group R or OR;

3. The process according to claim 2 wherein the bridge (R²₂A)_m is Si(CH₃)₂, SiPh₂, CH₂CH₂;
4. The process according to anyone of claims 1 to 3 wherein in the moiety of formula (IIa) T is sulphur.
5. The process according to anyone of claims 1 to 4 wherein R⁵, R⁶, R⁷, R⁸ and R⁹ are hydrogen.
6. The process according to anyone of claims 1 to 5 wherein the bridged metallocene compounds has formula (III)



(III)

wherein R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^7 , R^8 , A, T, M, X and m have the meaning reported in claim 1.

7. A 1-butene homopolymer having the following characteristics:
 - intrinsic viscosity (I.V.) > 0.7 dL/g
 - isotactic triads (mm) $> 70\%$;
 - 4,1 insertions $< 1\%$;
 - a flexural modulus (ASTM D 638) > 400 Mpa;
 - melting point $> 105^\circ\text{C}$.
8. The 1-butene homopolymer according to claim 7 wherein the isotactic triads (mm) are higher than 95%.
9. The 1-butene homopolymer according to anyone of claims 7-8 wherein the 4,1 insertions are comprised between 0.05% and 0.90%.
10. The 1-butene homopolymer according to anyone of claims 7-9 wherein the molecular weight distribution (M_w/M_n) is lower than 3.
11. A 1-butene/ethylene copolymer having a content of ethylene derived units from 0.1% to 5 % by weight in which the ethylene content in the polymer (C_2) and the melting point of

the polymer (T_m) meet the following relation:

$$T_m < -0.3283C_2^3 + 4.7184 C_2^2 - 22.454 C_2 + 114.$$

12. A 1-butene/ethylene copolymer having a content of ethylene derived units from 0.1% to 2.5 % by weight in which the ethylene content in the polymer (C_2) and the melting point of the polymer (T_m) meet the following relation:

$$T_m = 4.0037C_2^2 - 21.91C_2 + 114.$$

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/06575

A. CLASSIFICATION OF SUBJECT MATTER
 IPC 7 C08F10/08 C08F4/642

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	DE 199 03 306 A (TARGOR GMBH) 3 August 2000 (2000-08-03) claims 1,9-11,15 example 1 page 16, line 48	1-10
X	VATHAUER M ET AL.: "HOMOPOLYMERIZATIONS OF ALPHA-OLEFINS WITH DIASTEREOMERIC METALLOCENE/MAO CATALYSTS" MACROMOLECULES, AMERICAN CHEMICAL SOCIETY. EASTON, US, vol. 33, no. 6, 21 March 2000 (2000-03-21), pages 1955-1959, XP000932492 ISSN: 0024-9297 cited in the application page 1956, table 1, catalyst 2	1-3,5, 7-10

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the International filing date but later than the priority date claimed

- *T* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

7 October 2002

Date of mailing of the international search report

18/10/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Gamb, V

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/06575

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	<p>DATABASE WPI Derwent Publications Ltd., London, GB; AN 1991-203118 XP002215803 & JP 03 126704 A (IDEMITSU PETROCHEM CO), 29 May 1991 (1991-05-29) abstract</p> <p>---</p>	7-12
X	<p>DATABASE WPI Derwent Publications Ltd., London, GB; AN 1986-044999 XP002215804 & JP 60 262804 A (MITSUI PETROCHEM IND CO) , 26 December 1985 (1985-12-26) abstract</p> <p>---</p>	7-12
X	<p>EP 0 353 318 A (NESTE OY ; IDEMITSU PETROCHEMICAL CO (JP)) 7 February 1990 (1990-02-07) examples 1,4,5; table 1 example 2, comparative example 1; table 1</p> <p>---</p>	11,12
P,X	<p>WO 01 44318 A (BASELL TECHNOLOGY COMPANY B V ; EWEN JOHN A (US); ELDER MICHAEL J () 21 June 2001 (2001-06-21) claims 1,2,25,32,38 examples 1,2,4,6,7,54</p> <p>---</p>	1-10
P,X	<p>DATABASE WPI Derwent Publications Ltd., London, GB; AN 2002-291735 XP002215763 & WO 02 02659 A (MITSUI CHEM INC), 10 January 2002 (2002-01-10) abstract</p> <p>-----</p>	11,12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/06575

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 19903306	A	03-08-2000	DE 19903306 A1	03-08-2000
			BR 0004493 A	19-12-2000
			WO 0044799 A1	03-08-2000
			WO 0020466 A1	13-04-2000
			WO 0035973 A1	22-06-2000
			EP 1082363 A1	14-03-2001
			EP 1054914 A1	29-11-2000
JP 3126704	A	29-05-1991	NONE	
JP 60262804	A	26-12-1985	JP 1849211 C	07-06-1994
			JP 5059922 B	01-09-1993
EP 0353318	A	07-02-1990	CA 1319783 A1	29-06-1993
			JP 8016133 B	21-02-1996
			JP 63225605 A	20-09-1988
			EP 0353318 A1	07-02-1990
			CA 1309553 A1	27-10-1992
WO 0144318	A	21-06-2001	US 6444833 B1	03-09-2002
			AU 3007901 A	25-06-2001
			BR 0010043 A	22-01-2002
			CN 1347424 T	01-05-2002
			WO 0144318 A1	21-06-2001
			EP 1153047 A1	14-11-2001
			PL 349318 A1	15-07-2002
WO 0202659	A	10-01-2002	AU 6791501 A	14-01-2002
			WO 0202659 A1	10-01-2002